

Optimal Gradation Specifications

In order to ensure the aggregates will work optimally with Organic-Lock to create a strong and stable surface, it is important to ensure the aggregate meets our Optimal Gradation Specifications.

Gradation, in accordance with ASTM C136:

Optimal Gradation		
Sieve	Sieve Size (mm)	Percent Passing
3/8"	9.51	100%
4	4.76	80-100%
8	2.36	65-90%
16	1.18	40-60%
30	0.6	25-55%
50	0.3	15-35%
100	0.149	10-20%
200	0.074	5-15%